Answers for waterborne coatings & adhesives





Characteristics:	Aqueous, aliphatic polyurethane dispersion.	
Supplied as:	35% in water	
Physical characteristics:	Appearance	Translucence
	Non-volatile constituent	35±1 %
	PH value	7.5 - 9.5
	Viscosity	≤300mPa s
	Mean particle size	≤100 nm
	Glass transition temperature Tg	-25°C
	NMP, NEP, DMAC	Free
	Elongation	900-1000%
	Tensile strength	43.2Mpa
	100% Modulus	3.2Mpa
	Shear stability	good
	Dry	Fast
	Yellowing resistance	non- yellowing
Storage:	The dispersion should be stored in a frost-free place in tightly sealed containers.	
	It contains no preservative.	

Application:The coating has excellent adhesion on nylon, PVC, PET and other thin film
materials. Its film is transparent, and has high gloss, excellent water resistance,
abrasion resistance. Suitable for film printing, leather, textile, rubber and plastic
coating, etc.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.