

SiwoPUD[®] EC-600

Characteristics: Hydrophilic, aliphatic polyisocyanate.

Supplied as: 100%

Physical characteristics:	Appearance	Transparent
	Non-volatile constituent(%)	100
	Ionicity	Non-ionic
	NCO content	21.0±1 %
	Viscosity (mPa s)	1000-3000
	Density(d420)	1.07
	Monomeric diisocyanate content	≤0.2%

Storage: The crosslinker should be stored in tightly sealed containers, protected against frost and away from direct sunlight.

Application: The crosslinker can be thinned or dispersed in water, and mainly crosslinks the waterbased resins at room temperature (or high temperature). It has lower viscosity, and is especially for water-based adhesives and water-based printing paste, etc.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.