Answers for waterborne coatings & adhesives





Characteristics:	Nonionic, aqueous, aliphatic polyurethane dispersion based on polyester.	
Supplied as:	30% in water	
Physical characteristics:	Appearance	Translucence
	Non-volatile constituent	30±1 %
	Ionicity	Non-ionic
	PH value	6.0 - 7.5
	Viscosity	≤200 mPa s
	Mean particle size	≤100 nm
	Organic solvent	Free
	Glass transition temperature Tg	-25℃
	Elongation	500%
	Tensile strength	0.68Mpa
	100% Modulus	0.4Mpa
	Shear stability	good
	Yellowing resistance	non- yellowing
Storage:	The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.	
Application:	Nonionic aqueous polyurethane dispersion of high molecular weight. Its film is soft and elastic. It has good compatibility with cationic and anionic aqueous polyurethane dispersions, acrylic emulsions, or other ionic aqueous resin. It does not contain Restricted Substances in EU.	

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.

Contact: Brian Wei, SIWO US Inc, Duluth, GA. Tel: +1 859-333-9856/+86 19916703357, brianwei@siwo-us.com www.siwo-us.com