

SiwoPUD[®]-1216

Characteristics: Aqueous, aliphatic polyurethane dispersion based on polyester.

Supplied as: 30% in water

Physical characteristics:	Appearance	Translucence
	Non-volatile constituent	30±1 %
	Ionicity	Cationic
	PH value	3.5- 5.5
	Viscosity	≤50 mPa · s
	Mean particle size	≤100 nm
	NMP, NEP, DMAC	Free
	Shore A Hardness	68
	Shear stability	good
	Dry/touch	≤30min
	Dry/through	≤60min
	Yellowing resistance	non- yellowing

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

Application: Cost-effective product. Its film has good hardness, good abrasion resistance, heat resistance, good water resistance and resistance to salt spray. Mainly used for metal surface treatment, fiberglass infiltration agent, wood surface treatment etc. It does not contain Restricted Substances and Declarable Substances in EU.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.