

SiwoPUD- EC-602

Characteristics: Water-dispersible polyisocyanate crosslinker.

Hydrophilic, aliphatic polyisocyanate.

Supplied as: 100%

Physical characteristics: Appearance Transparent

Non-volatile constituent $100\pm1\%$

Ionicity Non-ionic NCO content $18.0\pm1\%$

Viscosity ≤8000mPa s

Density (d_4^{20}) 1.07

Monomeric diisocyanate content $\leq 0.2\%$

Storage: The crosslinker should be stored in tightly sealed containers, protected

against frost and away from direct sunlight.

Application:

The crosslinker can be thinned or dispersed in water, and mainly crosslinks the water-based resins at room temperature (or high temperature). It has higher viscosity, high crosslink density and quick-drying. Specifically for water-based adhesives, water based coatings.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.

Contact: Brian Wei, SIWO US Inc, Duluth, GA. Tel: +1 859-333-9856/+86 19916703357, brianwei@siwo-us.com www.siwo-us.com