

SiwoPUD[®]-FB-15

Characteristics:	Hydrophilic blocked aliphatic polyisocyanate	
Supplied as:	80%	
Physical characteristics:	Appearance	Colorless-light yellowish transparent
	Non-volatile constituent	80±2 %
	Ionicity	Non-ionic
	Blocked NCO content	8.0±1 %
	Viscosity	2000-10000mPa s
	Deblocking Temperature	100℃
Storage:	The crosslinker should be stored in tightly sealed containers, protected against frost and away from direct sunlight.	
Application:	It was developed as a hardener for water-diluent, one-component polyurethane stoving coatings with lower deblocked temperature. The properties of paint films formulated with it can be compared with conventional two-component polyurethane coatings via the degree of crosslinking and the choice of polyol. It was mainly used for water-based coatings and adhesives with high temperature baking conditions, etc. The resultant paint films are characterized by their high flexibility and hardness and their resistance to water and solvent.	

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.