

SiwoPUD-MATT-1901

Characteristics: Soft feel, inherent matte, aliphatic polyurethane dispersion.

Supplied as: 32% in water

Physical characteristics: Appearance Milky white

Non-volatile constituent 32 \pm 1 % PH value 7.0 - 9.5

Viscosity 1000-3000 mPa s

NMP, NEP, DMAC, etc. Free
Gloss at 60 ° ≤0.5
Elongation 500%
Tensile strength 29.6Mpa
Elasticity modulus (100%) 5.1Mpa

Yellowing resistance Non- yellowing

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers

and 5-38°C temperature conditions.. It contains no preservative.

Application: It provides soft touch and very low gloss. Gloss levels down to approximately 0.5

at 60° can be achieved. It has excellent matting performance, and good hydrolysis, abrasion resistance, adhesion. It also, in combination with alkaline soluble resins, results in outstanding print performance with enhanced soft feel properties. It can be added nitrogen pyridine crosslinker and water-dispersible polyisocyanate crosslinker to further improve the chemical resistance. Recommend for paper,

leather, textiles, and other coatings etc.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.

Contact: Brian Wei, SIWO US Inc, Duluth, GA. Tel: +1 859-333-9856/+86 19916703357, brianwei@siwo-us.com www.siwo-us.com www.siwo-us.com