

SiwoPUD[®]Ar128

Characteristics: Aqueous, aromatic polyurethane dispersion based on polyether.

Supplied as: 33% in water

Physical characteristics: Appearance milk to translucence

Non-volatile constituent 33 ±1 % PH value 7.0 - 9.5Viscosity (mPa s) ≤200 Mean particle size (nm) ≤100 Organic solvents (NMP,NEP) Free Elongation (%) 780 Tensile strength (Mpa) 12 Elasticity modulus (100% Mpa) 1.2

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers and

5-38°C temperature conditions. It contains no preservative.

Application: Its coating is soft and high elastic. Good water resistance, good alkali resistance.

Suitable for cohesive layer of synthetic leather and other applications.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.

Contact: Brian Wei, SIWO US Inc, Duluth, GA. Tel: +1 859-333-9856/+86 19916703357, brianwei@siwo-us.com www.siwo-us.com