

SiwoPUD[®]- Ar130

Characteristics: Aromatic, aqueous polyurethane dispersion based on polyester.

Supplied as: 35% in water

| | | |
|----------------------------------|--------------------------|--------------|
| Physical characteristics: | Appearance | Translucence |
| | Non-volatile constituent | 35 ±1 % |
| | PH value | 7.0 - 9.5 |
| | Viscosity | ≤300mPa s |
| | Mean particle size | ≤100 nm |
| | NMP, NEP, DMAC | Free |
| | Shore A Hardness | 90 |
| | Shear stability | good |
| | Dry | Fast |
| | Yellowing resistance | yellowing |

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

Application: Anionic aromatic polyurethane dispersion. It has high hardness, excellent resistance to heat and wear. It can be used for wood coatings and industrial coatings.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.