

SiwoPUD®-2013F

Characteristics: Aqueous, aliphatic polyurethane dispersion based on polycarbonate and polyester.

Supplied as: 45% in water

Physical characteristics: Appearance Translucence-white

Non-volatile constituent $45\pm1\%$ PH value 7.0-9.5 Viscosity $\leqslant 800 \text{mPa s}$

NMP, NEP, DMAC Free

Elongation 1000-1100%
Tensile strength 9.5Mpa
100% Modulus 1.0Mpa
Shear stability good
Dry Fast

Yellowing resistance non- yellowing

Storage: The dispersion should be stored in a frost-free place in tightly sealed containers. It

contains no preservative.

Application: The coating has good flexibility. It has excellent integrated performance. Its

coating exhibits excellent adhesion, abrasion resistance, UV and weathering resistance, excellent water resistance and waterproof performance. It is widely used in many industries such as elastic coatings, textile, synthetic leather, fabric

printing.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.

Contact: Brian Wei, SIWO US Inc, Duluth, GA. Tel: +1 859-333-9856/+86 19916703357, brianwei@siwo-us.com www.siwo-us.com