

## SiwoPUD<sup>®</sup>-U-9091

**Characteristics:** It is an aqueous anionic polyurethane dispersion based on polyester. It is a raw material for formulation of heat-activated adhesives.

**Supplied as:** 40% in water

<b>Physical characteristics:</b>	Appearance	Translucence to milky white
	Non-volatile constituent	40±1 %
	PH value	7.0 – 9.0
	Viscosity	≤800 mPa s
	Density(d <sub>4</sub> <sup>20</sup> )	1.05
	NMP, NEP, DMAC	Free
	Minimum film-forming temperature	5°C
	Minimum activation temperature	120°C
	Yellowing resistance	non- yellowing

**Storage:** The dispersion should be stored in a frost-free place in tightly sealed containers. It contains no preservative.

**Application:** Anionic high molecular weight polyurethane aqueous dispersion. Its film has high strength and heat-activation performance at high temperature. It is suitable for bonding wood, magnetic card manufacturing, plastic elastomer and other substrates.

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.